



Weatherproofing Tape

- Mastic and adhesive tape options
- Combined kits available

Adhesive Tape Options				
	Model Number	Thickness	Width	Length
	AWPT-A51W006-F	0.19 ± 0.01 mm	50.8 ± 0.5 mm	6000 ± 50 mm

Mastic Tape Options				
	Model Number	Thickness	Width	Length
	AWPT-M63W06M-F	2.5 ± 0.25 mm	63 ± 2.5 mm	600 ± 50 mm

Weatherproofing Tape Kit Options						
	Model Number	Included Products	Quantity	Thickness	Width	Length
	AWPTK-001	 Adhesive	1 each	0.19 ± 0.01 mm	50.8 ± 0.5 mm	6.0 ± 0.05 m
		 Adhesive	2 each	0.19 ± 0.01 mm	19 ± 0.5 mm	20 ± 0.05 m
		 Mastic	6 each	2.5 ± 0.25 mm	63 ± 2.5 mm	600 ± 50 mm

Quoted performance parameters are provided to offer typical, peak or range values only and may vary as a result of normal testing, manufacturing and operational conditions. Extreme operational conditions and/or stress on structural supports is beyond our control. Such conditions may result in damage to this product. Improvements to products may be made without notice.

Weatherproofing Tape

Adhesive Tape Characteristics		
Tensile Strength	≥ 3.5 kNm	
Elongation at Break	≥ 200%	
Breakdown Voltage	≥ 8 kV	
Adhesive Power	≥ 0.18 kV/m	
UV Resistance, minimum with no degradation	≥ 1,000 hours	
Weather Resistance Test Method	04AS00-03.6.0 / MIL-STD-1344A, Method 1002	
RoHS Compliant	Yes	
Mastic Tape Characteristics		
Heat Resistance	85° C (185° F) / 24 hour - No Liquid	
Elasticity	-17.8° C (0° F)	> 160%
	25° C (77° F)	> 170%
UV resistance, minimum with no degradation	Butyl test method in QUV weatherometer cycle of 8 hours UV at 65.6° C (150° F) then 4 hours of condensation at 40° C (104° F) / PVC tape test method UL 510, ASTM D1000	
RoHS Compliant	Yes	

Quoted performance parameters are provided to offer typical, peak or range values only and may vary as a result of normal testing, manufacturing and operational conditions. Extreme operational conditions and/or stress on structural supports is beyond our control. Such conditions may result in damage to this product. Improvements to products may be made without notice.